




# Test Report

## Hardness Test

Identification	Identification	ISO 48 - Micro IRHD Std
<b>Job :</b> (Generic) <b>Lot :</b> Lot 001 <b>Order :</b> Test 001 <b>Date :</b> 25/07/2005	<b>Product :</b> Gibitre Rubber R0705001 <b>Product Code :</b> R0705001 <b>Treatment :</b> Original State <b>Customer :</b> Customer 01 <b>Customer Code :</b> Cus001 <b>Operator :</b> Administrator	<b>Test Time</b> 30 sec

**Note 1**  
**Note 2**  
**Note 3**

**Note :**



	IRHD	a	r	k	As
	IRHD	Num	Num	Num	Num
<b>Lim.Max</b>	74.00				
<b>Lim.Min</b>	64.00				
<b>1</b>	68.37	-4.09	0.95	73.81	23.88
<b>2</b>	68.63	-5.15	1.00	75.41	18.16
<b>3</b>	68.42	-4.64	0.89	74.52	20.45
<b>Max</b>	68.63	-4.09	1.00	75.41	23.88
<b>Min</b>	68.37	-5.15	0.89	73.81	18.16
<b>Ave</b>	68.47	-4.63	0.95	74.58	20.83
<b>St.dev</b>	0.1380	0.5301	0.0551	0.8017	2.8789
<b>Cp</b>	12.08				
<b>Cpk</b>	13.35				

**Signature** \_\_\_\_\_

IRHD:IRHD; a;a; r;r; k;k; As:As;

