



# TEST REPORT

Customer **Customer 001**

Customer Code **84**

Printed: **24/08/2005**

Product **F235SR**

Product Code **292**

Page **1** of **3**

Order	Lot	Batch	ASTM D 2084 - Rheo OD 190°C					ASTM D 412 C - Traction Test				ASTM D 624 B - Tear Test
			ML	MH	Ts 2	t' 50	t' 90	TS	Ey	Se 100	Se 300	Ts
			dN*m	dN*m	mm:ss	mm:ss	mm:ss	N/mm2	%	N/mm2	N/mm2	N/mm
		Max Tol	27.48	81.23	0.51	1.31	1.52					
		Min Tol	22.48	66.46	0.41	1.15	1.32					
712	4372/5	1	22,41	73,47	0,59	1,48	2,12	20,81	606,75	1,62	6,86	0,00
		2	21,02	69,48	1,01	1,51	2,16	0,00	0,00	0,00	0,00	111,34
		3	22,40	69,81	1,04	1,51	2,16	0,00	0,00	0,00	0,00	0,00
		4	21,04	70,67	0,59	1,51	2,15	0,00	0,00	0,00	0,00	0,00
		5	22,16	68,07	1,03	1,47	2,11	0,00	0,00	0,00	0,00	0,00
		6	21,81	70,66	1,03	1,48	2,13	0,00	0,00	0,00	0,00	0,00
		7	21,97	69,78	1,04	1,49	2,15	0,00	0,00	0,00	0,00	0,00
		8	19,52	71,49	1,03	1,52	2,16	0,00	0,00	0,00	0,00	0,00
		9	21,01	70,17	1,03	1,53	2,18	0,00	0,00	0,00	0,00	0,00

