



# Report Test

## Density Test

Anagrafica	Identificazione	Density Check Std
<b>Commessa :</b> (Generic) <b>Ordine :</b> order y22 <b>Lotto :</b> lot 2 <b>Batch :</b> 1 <b>Data :</b> 28/07/2005	<b>Prodotto :</b> Gibitre Rubber R0705001 <b>Cod. prodotto :</b> R0705001 <b>Trattamento :</b> ASTM oil n° 1 <b>Cliente :</b> Customer 02 <b>Cod.Cliente :</b> cus002 <b>Operatore :</b> Administrator	<b>Liquido :</b> Distilled Water <b>Densità :</b> 0.99780 <b>g/cm3</b>

Note :

N° Test	Mass mg	Vol mg	Dens g/cm3	Mass_Trtr mg	Vol_Trtr mg	Dens_Trtr g/cm3	Delta-M% %	Delta-V% %
Lim.Max			1.2877				-2.44	-2.38
Lim.Min			1.0535				-2.98	-2.92
1	4253.8	3635.7	1.17	3926.30	3353.88	1.1707	-7.70	-7.75
2	4698	4013.33	1.1706	4511.50	3853.98	1.1706	-3.97	-3.97
3	4097.8	3500.5	1.1706	4087.00	3492.48	1.1702	-0.26	-0.23
Max	4698.00	4013.33	1.1706	4511.50	3853.98	1.1707	-0.26	-0.23
Min	4097.80	3500.50	1.1700	3926.30	3353.88	1.1702	-7.70	-7.75
Ave	4349.87	3716.51	1.1704	4174.93	3566.78	1.1705	-3.98	-3.98
St.dev	311.4188	265.7939	0.0003	302.3474	258.1964	0.0003	3.7200	3.7600
Cp			112.66				0.02	0.02
Cpk			112.85				0.14	0.14

Firma \_\_\_\_\_

