




Report Test

LowTemperatureCheck

Identification		Identification		ISO 2921 - Temperature	
Job :	(Generic)	Product :	Compound 01	Conditioning Time	10 min
Order:	test cal	Product Code :		Immersion temperature	-70 °C
Lot :	cal	Treatment :		Test Start Temperature	-65 °C
		Customer :	Customer 01	Final Temperatura	0 °C
		Customer Code :		Temperature Gradient	1 °C
Data :	20/12/2005	Operatore :	Administrator		

Notes : ShoreA Hardness
IRHD Hardness
Density [g/cm3]



Batch/NSam	TR 10 °C	TR 30 °C	TR 50 °C	TR 70 °C	DTR 10-70 °C	t 10 min	t 30 min	t 50 min	t 70 min
Max Tol	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Min Tol	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
■ 1/1	-16.20	-12.70	-10.30	-7.50	8.70	48.26	51.73	54.14	57.03
■ 1/2	-16.30	-12.70	-10.20	-7.30	9.00	48.17	51.70	54.19	57.17
■ 1/3	-16.30	-12.70	-10.30	-7.40	8.90	48.17	51.70	54.18	57.16
■ 1/4	-16.40	-12.80	-10.30	-7.50	8.90	48.05	51.60	54.09	56.98
■ 1/5	-16.50	-12.90	-10.40	-7.60	8.90	47.96	51.52	53.97	56.84
■ 1/6	-16.50	-12.90	-10.60	-7.70	8.80	47.97	51.47	53.87	56.71
Max	0.00	0.00	0.00	0.00	9.00	48.26	51.73	54.19	57.17
Min	-16.50	-12.90	-10.60	-7.70	8.70	47.96	51.47	53.87	56.71
Ave	-16.37	-12.78	-10.35	-7.50	8.87	48.10	51.62	54.07	56.98
St.dev	0.1211	0.0983	0.1378	0.1414	0.1033	0.1219	0.1075	0.1279	0.1808
Cp	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Cpk	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00

Signature _____

