




Test Report

Hardness Test

| Identification | | Identification | | ISO 48 - Micro IRHD Std | |
|----------------|------------|------------------------|-------------------------|-------------------------|--------|
| Job : | (Generic) | Product : | Gibitre Rubber R0705001 | Test Time | 30 sec |
| Lot : | Lot 001 | Product Code : | R0705001 | | |
| Order : | Test 001 | Treatment : | Original State | | |
| Date : | 25/07/2005 | Customer : | Customer 01 | | |
| | | Customer Code : | Cus001 | | |
| | | Operator : | Administrator | | |

Note 1
Note 2
Note 3

Note :



| | IRHD | a | r | k | As |
|----------------|--------|--------|--------|--------|--------|
| | IRHD | Num | Num | Num | Num |
| Lim.Max | 74.00 | | | | |
| Lim.Min | 64.00 | | | | |
| 1 | 68.37 | -4.09 | 0.95 | 73.81 | 23.88 |
| 2 | 68.63 | -5.15 | 1.00 | 75.41 | 18.16 |
| 3 | 68.42 | -4.64 | 0.89 | 74.52 | 20.45 |
| Max | 68.63 | -4.09 | 1.00 | 75.41 | 23.88 |
| Min | 68.37 | -5.15 | 0.89 | 73.81 | 18.16 |
| Ave | 68.47 | -4.63 | 0.95 | 74.58 | 20.83 |
| St.dev | 0.1380 | 0.5301 | 0.0551 | 0.8017 | 2.8789 |
| Cp | 12.08 | | | | |
| Cpk | 13.35 | | | | |

Signature _____

IRHD:IRHD; aa; rr; kk; As:As;

