




Test Report

Identification		Identification		ISO 48 - Micro IRHD -	
Job	(Generic)	Product	Compound 01	Test Time (Max 90 sec)	30 sec
Order	1	Product Code	001	Hysteresis Time (Max 90s)	30 sec
Lot	1	Treatment	Original State		
Date :	21/07/2009	Customer	Customer 01		
		Customer Code	Cus001		
		User	Administrator		

ShoreA Hardness
IRHD Hardness
Density [g/cm3]

Notes



	IRHD 30	Hyst 30
	IRHD	IRHD
Max.Tol		
Min. Tol.		
■ 1	67.0	98.0
■ 2	66.9	97.8
■ 3	67.3	97.9
■ 4	68.4	98.6
Max	68.40	98.60
Min	66.90	97.80
Ave	67.40	98.08
St.dev	0.6880	0.3594
Cp		
Cpk		

Signature

IRHD:IRHD_Hardness_at_time; Hyst:Hysteresis;

